



PRODUCT DATA SHEET

Description

AMPUR – MP 3 FLOORING - four-component, fast-curing, self-flowing composite material based on water dispersion process, modified polyisocyanates liquid pigment and reactive fillers.

Use

AMPUR – MP 3 FLOORING – used for colourant, non-slip, high performance floorings in AMPUR MP POUR and BROADCAST FLOORING SYSTEM

Mixture properties and components ratio

	AMPUR - MP 3 FLOORING			
Stage	Appearance	Quantity	Density	Viscosity
Component A	Milky-white, low viscosity liquid	3,00	0,95	250
Component B	Clear, brown, low viscosity liquid	3,50	1,2	100
Component C	Reactive filler	12,5	1,25	powder
Component D	Colourant, medium viscosity liquid	1,0	1,75	250
Mixture	Colourant, fluid, self-flowing mass	20,00	1,85	2500

Material preparation

Prepare the mixing area and a proper amount of AMPUR – MP 3 FLOORING

Pre-mix the component A by shaking vigorously, open the caps.

Put component A, B, and D simultaneously into a clean and high container (~15 dcm3 capacity)

Mix the liquid components with a high-speed stirrer (800 – 1000 rpm)

Put into another container (30 dm3) and add the component C while mixing, then mix again to obtain a homogeneous substance (approx. 800 rpm, for 2 - 3 min.)

Pour the material immediately and apply on the prepared substrate, then smooth.

Open time (processing and treatment): approx. 10 - 15 min.

Close empty containers and return either to the manufacturer or for reclamation/disposal.

Application

Do not apply on wet and dirty surfaces or if there is a risk of vapour condensation.

Apply prepared material on the substrate, spread into an even layer with metal floats. If necessary, level the texture with a short-nap roller. The above activities should be carried out within 10- 15 min., otherwise the material will no longer be suitable for use.

Skim any remains from the package into a metal waste disposal bucket

Material performance and consumption

Material consumption is conditioned by substrate roughness, temperature and tools being used

Normal consumption: approx. 6,5 kg/m2, (for 3,5 mm thickness).

Performance: one package (20,0 kg) should be sufficient to make approx. 3,0 m2 flooring, (for 3,5 mm thickness).

Cleaning

If the need arises for cleaning substrate or unhardened material tools, proper organic solvents (e.g. xylene) or cleaning cloths can be used. It is advisable that cleaning activities are performed outside the working area, in a specially designated area. After material hardening, contaminations become insoluble, but they can be subjected to mechanical cleaning.

Health and Safety notes

Each material and component is supplied with a Safety Card.

It is recommended that safety glasses, gloves and anti-dust masks are used during material application, handling and mixing.

Storage

All Ampur materials should be stored in a dry and shady area.

Optimum temperature: 10 – 25 °C.

Prior to use, the substrate, ambient conduins and quality of the materials should be inspected. In case of any doubts or non-standard use, please consult our sales representatives. This document remains effective until the new version is issued.

Issue date: 01.01.2014



PPHU AMPUR Piotr Mundzia guarantees a high quality of products and takes responsibility for any damages to the materials supplied. However, operating and ambient conditions, as well as material preparation and application are beyond our control, hence, no liability is expressed in terms of the final effect of the materials used at the Construction Site, All materials can be used only by trained and experienced Staff, in accordance with application and ambient recommendations specified in the Application Manual for AMPUR MP Materials. All the information and recommendations are based on our extensive knowledge and experience.